

HARDNESS CONVERSION TABLE

ROCKWELL C - BRINELL

Rockwell C	Brinell	Rockwell C	Brinell	Rockwell C	Brinell
	145	19	220	44	419
	146	20	225	45	430
	148	21	230	46	442
	150	22	235	47	453
	152	23	241	48	464
	154	24	247	49	476
	156	25	253	50	488
1	158	26	259	51	500
2	160	27	265	52	512
3	162	28	272	53	524
4	165	28	279	54	536
5	168	30	286	55	548
6	171	31	294	56	561
7	174	32	301	57	574
8	177	33	309	58	587
9	180	34	318	59	600
10	183	35	327	60	613*
11	186	36	337	61	627*
12	190	37	347	62	638*
13	193	38	357	63	652*
14	197	39	367	64	670*
15	201	40	377	65	685*
16	206	41	387	66	700*
17	210	42	398		
18	215	43	408		

* approx.